



BAKING[®]PLUS

BAKING PAPER FOR PROFESSIONALS

Stand: 01/2026

BAKINGPLUS 35-43 gsm DATENBLATT / Technical Datasheet*			
Spezifikationen/Specification		35gsm-43gsm double silicone coated baking paper 35gsm-43gsm Backtrennpapier, beidseitig silikonisiert	
PARAMETER	UNIT/EINHEIT	REFERENZ/REFERENCE	STANDARD
Grammatur/Substance	g/sqm	Tolerance: «2g	ISO536: 2012(E)
Dicke/Thickness	µm	35-60	ISO534:2011(E)
Format/Size	mm	«2mm	GB/T 451.1
Reißfestigkeit/Tear Strength			
MD	mN	≥130	ISO 1974:2012(E)
CD	mN	≥140	ISO 1974:2012(E)
Zugfestigkeit/Tensile Strength			
MD	KN/m	≥1.8	ISO 1924-2:2008(E)
CD	KN/m	≥0.8	ISO 1924-2:2008(E)
Wasseraufnahme/Water Absorptiveness (Cobb 60S)	g/m ²	≤25	ISO 535:2014(E)
Hitzebeständigkeit/Heat Resistance	°C	≥230	20 min. im Backofen/Baking in the oven for 20 minutes
Trennkraft/Release Force	kgf/cm	20-70	GBT2792
Schmutzpartikel/Dirt Count			
<2.0mm [↗]	↑/m ² pcs/m ²	≤100	GB/T 1541
2.0mm [↗] ~3.0mm [↗]		≤10	GB/T 1541
>3.0mm [↗]		0	GB/T 1541
Geruch/Odour	Grade	≤1	EN1230 Part1
Fluoreszierende Substanzen/Fluorescent substance			
254nm	/	negative/Negative	GB31604.47-2016
365nm	/	negative/Negative	GB31604.47-2016
Dyne-Wert/Dyne Value	/	≤34	Dyne Pen

*technische Änderungen vorbehalten / *Subject to technical modifications without prior notice

PRIME PAPERS INTERNATIONAL GmbH
Poststraße 8-10
DE-23669 Timmendorfer Strand
Tel: +49 4503 76 239 76 00

E-mail: sales@primepapers.de
VAT-No. DE450286495
TAX-No. 22 295 503 66
Registration: Amtsgericht Lübeck, HRB 25588 HL